

Dulux AcraTex 951 Coventry Coarse Sand Finish

AUDA1065

Part A	194-85753	Image	
--------	-----------	-------	--

Product Overview

Previously known as DULUX AcraTex 951 Coventry Coarse
DULUX AcraTex 951 Coventry Coarse is a decorative, low build protective coating displaying excellent resistance to weathering and atmospheric chemicals. The finish will resemble that of a coarse granular render which is sponge floated.

19485753 Coventry Coarse
19485754 Coventry Coarse Winter Grade
19485944 Coventry Coarse Accent Base
19486074 Coventry Coarse Accent Base Winter Grade
19485757 Coventry Coarse Extra Bright

Features And Benefits

- | | |
|--|--|
| <ul style="list-style-type: none"> ▪ Long 'wet edge' Standard Grade ▪ Faster Dry "Accent Base Winter Grade" ▪ Available in Standard, Accent & Extra Bright base's ▪ Even granular appearance | <ul style="list-style-type: none"> ▪ Easy to apply ▪ Improved productivity in colder weather ▪ Extended Colour Range ▪ Tough |
|--|--|

Uses And Typical Specifications

Uses	For interior/exterior application to both new and old masonry. DULUX AcraTex 951 Coventry Coarse is trowel applied and finished to achieve an even coarse granular appearance.																																						
Typical Systems	<p>Typical System AUSA5059 Renderwall/ GRS/ Cov Coarse/ AcraShield for New Concrete Block</p> <p>Preparation Guide PBK019 - BRICK / BLOCKWORK AND MASONRY</p> <p>ASSESS SUITABILITY</p> <p>Concrete, mortar and cement based products need to be fully cured for at least 28 days before painting.</p> <p>REMOVE POWDER LAYERS & EFFLORESCENCE</p> <p>Remove any powdery layers, laitance or efflorescence by detergent cleaning, wire brushing, water blasting or a suitable chemical treatment.</p> <p>CLEAN</p> <p>Clean the surface thoroughly by water blasting or detergent cleaning, where a commercial cleaner is added to hot or cold water and surface is washed / scrubbed thoroughly with a stiff bristle broom and then rinsed clean with fresh water. This may need to be repeated on extremely dirty surfaces to ensure removal of efflorescence or other poorly bonded surface material. Ensure that the surface is dry, clean and free from dust.</p> <table> <tr> <th>Coat</th><th>Product</th><th>Spread Rate (m²/L)</th><th>WFT (micron)</th><th>DFT (micron)</th></tr> <tr> <td>Prep Coat</td><td>Renderwall</td><td>0.3</td><td>4000</td><td>4000</td></tr> <tr> <td>1st Coat</td><td>Green Render Sealer</td><td>8.0</td><td>127</td><td>44</td></tr> <tr> <td>2nd Coat</td><td>951 Coventry Coarse</td><td>0.8</td><td>1333</td><td>1000</td></tr> <tr> <td>3rd Coat</td><td>955 AcraShield</td><td>6.0</td><td>167</td><td>75</td></tr> <tr> <td>Optional</td><td>955 AcraShield</td><td>6.0</td><td>167</td><td>75</td></tr> <tr> <td colspan="4">Minimum System DFT</td><td>5119</td></tr> </table> <p>Notes Do not apply paint if Relative Humidity is above 85% or temperature is within 3°C of Dew Point.</p> <p>Do not apply if the surface temperature is greater than 40°C or below 10°C, or likely to fall below 10°C during the application or drying period.</p> <p>Do not apply paint if the temperature is below 10°C or likely to fall below 10°C during the drying period.</p> <p>This specification must be read in conjunction with the appropriate technical data sheets.</p> <p>CEMENT RENDERS PRODUCE FINE CRACKS DURING DRYING AND CONTINUE TO CRACK & MOVE WITH VARIATIONS IN TEMPERATURE. FOR ENHANCED PERFORMANCE USE A HIGH BUILD ELASTOMERIC (FLEXIBLE) COATING. DULUX RECOMMENDS THE USE OF DULUX ACRASHIELD 955.</p> <p>At Commencement of coating system application to the substrate it shall be deemed that the Applicator has certified that the surface which it is to be applied to is fit receive this specified coatings system.</p> <p>When the Applicator is preparing the site sample for approval he should advise the Project Superintendent if the substrate condition is not of sufficient standard to produce the specified finish.</p> <p>A DULUX warranty will be provided confirming protection against flaking & peeling for a period of Seven years extended to Fifteen years when a full AcraTex system including 2 coats of AcraShield is applied by a DULUX AcraTex trained applicator, according to specification, & at the specified spreading rates, & to the surface preparation details described in the DULUX AcraTex Specification Manual.</p>				Coat	Product	Spread Rate (m ² /L)	WFT (micron)	DFT (micron)	Prep Coat	Renderwall	0.3	4000	4000	1st Coat	Green Render Sealer	8.0	127	44	2nd Coat	951 Coventry Coarse	0.8	1333	1000	3rd Coat	955 AcraShield	6.0	167	75	Optional	955 AcraShield	6.0	167	75	Minimum System DFT				5119
Coat	Product	Spread Rate (m ² /L)	WFT (micron)	DFT (micron)																																			
Prep Coat	Renderwall	0.3	4000	4000																																			
1st Coat	Green Render Sealer	8.0	127	44																																			
2nd Coat	951 Coventry Coarse	0.8	1333	1000																																			
3rd Coat	955 AcraShield	6.0	167	75																																			
Optional	955 AcraShield	6.0	167	75																																			
Minimum System DFT				5119																																			

Precautions And Limitations

A minimum spread rate of 0.8 square metres per litre is required.

Do not apply externally in temperatures below 10C or when the temperature of the surface may fall below 10C during the drying period.

When the weather is doubtful avoid application.

Must be protected from rain and frost for the first 24 hours.

Avoid application in hot, windy conditions or on hot surfaces.

To ensure colour uniformity and for optimum performance topcoat with DULUX AcraTex 955 AcraShield. Ensure that you have adequate tinted stock to complete the job in one application.

All material must be thoroughly cross-mix to ensure tint uniformity.


Check colour prior to application.

IMPORTANT: Not all colours are suitable for exterior use.

DULUX AcraTex 951 Coventry Coarse is not suitable for roller or spray applied finishes.

Performance Guide

Weather	Excellent resistance to cracking, flaking and chalking as part of a full system.	Salt	Resists salt spray especially when topcoated with DULUX AcraTex 955 AcraShield.
Heat Resistance	Up to 90C (dry)	Water	Water resistant with good vapour permeability.
Solvent	Resists alcohol and aliphatic hydrocarbons. Sensitive to strong solvents.	Abrasion	Good resistance to abrasion especially when topcoated with DULUX 955 AcraTex AcraShield.
Acid	Slight softening with dilute acid. Inert when topcoated with DULUX AcraTex 955 AcraShield.	Alkali	Slight softening with dilute alkali. Inert when topcoated with DULUX AcraTex 955 AcraShield.

Typical Properties																											
V.O.C Content	< 35 g/L untinted		Clean Up Clean up water																								
Application Method	 Trowel																										
Application Conditions	<table> <tr> <td>Solids By Volume</td><td>75</td><td></td><td></td></tr> <tr> <td></td><td>Min</td><td>Max</td><td>Recommended</td></tr> <tr> <td>Wet Film Per Coat (microns)</td><td>1333</td><td>1467</td><td>1333</td></tr> <tr> <td>Dry Film Per Coat (microns)</td><td>1000</td><td>1100</td><td>1000</td></tr> <tr> <td>Recoat Time (min)</td><td>24 hours</td><td>Indefinite</td><td></td></tr> <tr> <td>Theoretical Spread Rate (m²/L)</td><td>0.8</td><td>0.7</td><td>0.8</td></tr> </table>			Solids By Volume	75				Min	Max	Recommended	Wet Film Per Coat (microns)	1333	1467	1333	Dry Film Per Coat (microns)	1000	1100	1000	Recoat Time (min)	24 hours	Indefinite		Theoretical Spread Rate (m²/L)	0.8	0.7	0.8
Solids By Volume	75																										
	Min	Max	Recommended																								
Wet Film Per Coat (microns)	1333	1467	1333																								
Dry Film Per Coat (microns)	1000	1100	1000																								
Recoat Time (min)	24 hours	Indefinite																									
Theoretical Spread Rate (m²/L)	0.8	0.7	0.8																								
Typical Properties Notes	<p>Application Procedure and Equipment Product should be thoroughly mixed before use. Refer to the DULUX AcraTex Application Manual for detailed application instructions. DULUX AcraTex 501/1 AcraPrime Water Based may be applied by roller, conventional or airless spray. A brush is required to cut in around edges and obstacles. Typical airless set-up: Graco Ultra 500 using 0.011-0.013 spray tip at approx. 1000 psi. Brush, roller, conventional or airless spray.</p>																										

Application Guide	
Surface Preparation	<ul style="list-style-type: none"> Ensure alkaline surfaces have aged for 30 days minimum. <p>All surfaces must be thoroughly clean and free of all contaminants, dirt, surface chalk, grease, mould, mildew, wax, loose or flaky paint, form oils, release agents and mortar splashes. Metal, tie wire, etc. on surface must be removed or treated against corrosion. Surface imperfections and irregularities should be levelled and patched and completely flush to surrounding surfaces. Maximum coverage and durability is assured by first using DULUX AcraTex AcraPrime Water Based.</p>
Application Procedure And Equipment	<ul style="list-style-type: none"> Product should be thoroughly mixed before use. <p>Refer to the DULUX AcraTex Application Manual for detailed application instructions. Use masking to protect adjacent areas. The area should be patched and primed ready for final texture coat. DULUX AcraTex 951 Coventry Coarse is applied by hawk and stainless steel trowel, then finished in a circular motion with the plastic finishing float to achieve an even granular appearance. Two applicators are required for most areas - one applying the other processing the finish. Delivery must be to a uniform thickness. Allow the material to stand for a short time before "rubbing up" with float to produce the desired pattern/texture. Application must be in a brisk uniform fashion terminating when the whole area is complete, banded by a natural break such as an expansion joint, corner etc. Application commenced on a single area must be completed uninterrupted.</p> <ul style="list-style-type: none"> Trowel and Hawk finished with a plastic float

Health And Safety			
MSDS Number	10965	Health Effects	<p>For detailed information refer to product label and the current Material Safety Data Sheet available through Dulux Sales and Customer Service offices 132377 AUS.</p> <p>For detailed information refer to product label and the current Material Safety Data Sheet available through Dulux Sales and Customer Service offices 132377 AUS.</p> <p>Health Effects: Splashes to the eye may cause eye irritation.</p> <p>Personal Protective Equipment: Wear eye protection.</p>
In the case of emergency, please call 1800 033 111			

Transport And Storage	
Pack A	194-85753
Size 15 Litre	Weight 23.5kg

Images



Disclaimer

Dulux and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "AcraTex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427